


# LANSORB UV-944

## Light Stabilizer 944

CAS No. 71878-19-8

Specifications:



Tests	Specification
Appearance	White to light-yellow particles
Color	≤120
Softening point	110~130°C
Volatiles	≤1.0%
Ash	≤0.1%
Light transmittance (425nm)	≥93.0%
Light transmittance (500nm)	≥95.0%

**Package:** 25Kg/Carton

**Application:**

- The product is suitable for various polymer materials such as polyolefin materials, cross-linked polyethylene, olefin copolymers, PS, PA, PU, flexible PVC etc., especially thin products and silk fabrics.

**Storage:** Keep container tightly closed in a dry and well-ventilated place.

**Recommend Shelf Life:** 12 months.